



# TECHNICAL SPECIFICATIONS



# TECHNICAL SPECIFICATIONS

Material: Quartz  
Thickness: 2 cm

S.No	Test Parameters	Test Results	Test Method
------	-----------------	--------------	-------------

## A MECHANICAL TESTING

1.	Water Absorption, % by mass	0.04	ASTM C 97
2.	Apparent Density, g/cm <sup>3</sup>	2.406	ASTM C 97
3.	Moh's Hardness	7	ASTM C 1895
4.	Flexural Strength, MPa	-	ASTM C 880
	Dry Condition	66.2	
	Wet Condition	78.5	
5.	Co-efficient of Linear Thermal Expansion, °C <sup>-1</sup>	4.8 X 10 <sup>-6</sup>	ASTM C 372
6.	Abrasion Resistance, H	31.1	ASTM C 241

## B. CHEMICAL TESTING

7.	Resistance to Staining	Not Affected	ASTM C 1378
----	------------------------	--------------	-------------



# TECHNICAL SPECIFICATIONS

Material: Cristobalite  
Thickness: 3 cm

S.No	Test Parameters	Test Results	Test Method
------	-----------------	--------------	-------------

## A MECHANICAL TESTING

1.	Water Absorption, % by mass	0.03	ASTM C 97
2.	Apparent Density, g/cm <sup>3</sup>	2.145	ASTM C 97
3.	Moh's Hardness	7	ASTM C 1895
4.	Flexural Strength, MPa	-	ASTM C 880
	Dry Condition	67.3	
	Wet Condition	91.1	
5.	Co-efficient of Linear Thermal Expansion, °C <sup>-1</sup>	4.8 X 10 <sup>-6</sup>	ASTM C 372
6.	Abrasion Resistance, H <sub>a</sub>	29.4	ASTM C 241

## B. CHEMICAL TESTING

7.	Resistance to Staining	Not Affected	ASTM C 1378
----	------------------------	--------------	-------------